

Nominal Diameter	Outside Diameter	Cement Lining Thickness	Wall Thickness	Maximum Test Pressure
(mm)	(mm)	(mm)	(mm)	(Bars)
100	114.3	6.0	3.6	70.0
125	139.7	6.0	3.6	70.0
150	168.3	6.0	3.6	70.0
175	193.7	10.0	4.0	70.0
200	219.1	10.0	4.0	70.0
225	244.5	10.0	4.0	70.0
250	273.0	10.0	4.0	64.5
300	323.9	10.0	4.0	54.3
350	355.6	13.0	4.5	55.7
400	406.4	13.0	4.5	48.7
450	457.0	13.0	5.0	48.2
500	508.0	13.0	5.0	43.4
550	559.0	13.0	6.3	49.6
600	610.0	13.0	6.3	45.4
650	660.0	19.0	6.3	42.1
700	711.0	19.0	6.3	39.0
750	762.0	19.0	6.3	36.3
800	813.0	19.0	7.1	38.4
850	864.0	19.0	7.1	36.2
900	914.0	19.0	7.1	34.2
1000	1016.0	19.0	7.1	30.7
1200	1219.0	19.0	8.0	28.8
1400	1420.0	25.0	8.8	27.2
1600	1626.0	25.0	11.0	27.0
1800	1829.0	25.0	11.0	26.4
2000	2032.0	25.0	12.5	27.0
2200	2235.0	25.0	14.2	28.0